

## TECHNICAL DATASHEET

## **ECOGREASE CA2**

## **Typical properties:**

NLGI 2 Soap type Ca

Worked penetration 265 - 295

Dropping point °C 130

Application range °C -40 / +90

Emcor corrosion test 1 / 2

Copper corrosion

24 hr/ 100°C 0

Four Ball wear test N 1800

Mineral oil specs.

Viscosity at 40°C cSt 22

Base oil type rapeseed

DO NOT MIX ECO GREASE Ca 2 WITH OTHER GREASES DO NOT USE FOR WHEEL BEARINGS OR WATER PUMPS

## **General information:**

Rapeseed oil based calcium-soap grease. Environmentally harmless and rapidly biodegradable. Agricultural and constructional machinery and equipment which should be greased with conventional NLGI 2 Lithium soap, multipurpose grease via nipples or at open lubrication points. As a rule these are mechanical arm joints, chains, plain bearings, exposed gears, towing hitches, battery terminals, etc... When using ECO GREASE Ca 2 for the first time, pump the grease through the bearing until it extrudes past the seal or out of the vent.

Average analysis, without engagement

TCS 08/04